
**UNITED STATES
SECURITIES AND EXCHANGE COMMISSION**

Washington, D.C. 20549

FORM 6-K

**REPORT OF FOREIGN PRIVATE ISSUER PURSUANT TO RULE 13a-16 OR 15d-16
UNDER THE SECURITIES EXCHANGE ACT OF 1934**

For the month of **March 2023**

Commission File Number: **001-41065**

SNOW LAKE RESOURCES LTD.

(Translation of registrant's name into English)

**242 Hargrave Street, #1700
Winnipeg, Manitoba R3C 0V1 Canada**
(Address of principal executive offices)

Indicate by check mark whether the registrant files or will file annual reports under cover Form 20-F or Form 40-F.

Form 20-F Form 40-F

Indicate by check mark if the registrant is submitting the Form 6-K in paper as permitted by Regulation S-T Rule 101(b)(1):

Indicate by check mark if the registrant is submitting the Form 6-K in paper as permitted by Regulation S-T Rule 101(b)(7):

SUBMITTED HEREWITH

<u>Exhibit</u>	<u>Description</u>
99.1	News Release dated March 16, 2023

SIGNATURES

Pursuant to the requirements of the Securities Exchange Act of 1934, the registrant has duly caused this report to be signed on its behalf by the undersigned, thereunto duly authorized.

SNOW LAKE RESOURCES LTD.
(Registrant)

Date: March 16, 2023

By: */s/ Keith Li*

Keith Li
Title: Chief Financial Officer



Metallurgical Test Results Demonstrates Excellent Recovery and Produces High Grade Spodumene Concentrate

Highlights:

- Metallurgical testwork from the Grass River Project demonstrates 83.5% lithium recovery producing a 6.39% Li₂O spodumene concentrate.
- Mineral Resource Estimates for both the Thompson Brothers and Grass River Projects are forthcoming.
- The Company's PEA study is well advanced and is expected to be finalized in Q2 2023.
- CEO search well underway, with high quality and experienced candidates already shortlisted.

Snow Lake Lithium (Snow Lake or the Company) is pleased to announce the results of a metallurgical testwork program conducted for its Grass River Lithium Project.

SGS Canada were engaged to conduct the study on behalf of the Company, with a metallurgical target of producing a spodumene concentrate grading >6% Li₂O and <1.0% Fe₂O₃ while maximising recovery. The Company is pleased to announce that these targets have been achieved with the developed flowsheet showing an 83.5% lithium recovery.

Commenting on the results of the metallurgical study, Snow Lake's Chairman Mr Nochum Labkowski said *"These metallurgical results from our Grass River project are tremendously encouraging with the high recovery levels demonstrating the significant commerciality of our project."*

Following the previously announced strategic review of the Company's operations we have been committed to moving our projects along the development pipeline as quickly as possible. Together with our soon to be announced mineral resource estimates, these metallurgical results will feed into our PEA which in turn will provide us with a clear pathway towards production.

As has been previously announced, the PEA will consider launching the project with a DSO operation, thereby bringing forward cashflows whilst minimising upfront capital expenditures. DSO is a proven method of enabling a company to transition a lithium mine from initial development to producing a concentrate as has been recently demonstrated by [Core Exploration \(ASX:CXO, OTC:CXOXF\)](#)

The next few months promises to be a very exciting time for our Company as we continue to unlock the value of our project."

Samples from the Grass River Lithium Deposit near Snow Lake, Manitoba were received at SGS Lakefield for a scoping level metallurgical testwork program on a main composite sample made from pegmatite and waste rock samples. Prior to compositing, all samples were crushed and screened to remove the -1/2 inch (-12.7 mm) and the -3/8 inch (-9.5 mm) fractions as they were not suitable for ore sorting. The coarse fraction was then sent to Steinert for ore sorting testwork. The resulting ore sorting products and the -1/2 inch and -3/8 inch fractions were combined later to produce the main composite sample for this testwork program. This program included sample preparation, head sample characterization, grindability, heavy liquid separation (HLS), dense media separation (DMS), dry magnetic separation and batch flotation testing.

The objective of the program was to evaluate the previously developed flowsheet on a larger scale and produce a larger amount of concentrate. The metallurgical target was the production of spodumene concentrate grading $> 6.0\%$ Li₂O and $< 1.0\%$ Fe₂O₃, while maximizing lithium recovery.

The assays of the combined pegmatite and waste material as received and after crushing and classification for ore sorting are shown in Table I. Lithium and iron assays in the composite head sample were 1.24% Li₂O and 2.08% Fe₂O₃, respectively.

Table I: Assays of the Combined Head Sample (Pegmatite and Waste) and Classified Size Fractions Prior to Ore Sorting

Streams	Mass	Assay %									Distribution %								
	%	Li ₂ O	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	P ₂ O ₅	Li ₂ O	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	P ₂ O ₅
Composite Head Sample	100	1.24	71.2	16.2	2.08	0.48	1.16	4.28	1.74	0.14	100	100	100	100	100	100	100	100	100
Waste Head Sample	17.6	0.21	60.2	16.0	8.49	1.88	5.01	2.90	2.51	0.23	3.0	14.8	17.3	71.6	68.0	75.8	11.9	25.3	28.4
Pegmatite Head Sample	82.5	1.46	73.5	16.3	0.72	0.19	0.34	4.57	1.58	0.12	97.0	85.2	82.7	28.4	32.0	24.2	88.1	74.7	71.6
Coarse (+1/2") Waste Frac	16.7	0.22	60.2	16.0	8.43	1.86	4.97	2.90	2.55	0.23	2.9	14.1	16.5	67.8	64.1	71.6	11.3	24.5	27.2
Fine (-1/2") Waste Frac	0.8	0.15	59.0	15.5	9.64	2.24	5.81	2.87	1.70	0.20	0.1	0.7	0.8	3.9	3.9	4.2	0.6	0.8	1.2
Coarse (+1/2") Peg Frac	68.0	1.62	73.4	16.7	0.68	0.17	0.32	4.54	1.53	0.13	88.8	70.1	70.0	22.2	23.2	19.0	72.2	59.8	60.7
Fine (-1/2") Peg Frac	14.4	0.71	74.2	14.2	0.88	0.30	0.42	4.73	1.80	0.11	8.2	15.0	12.6	6.1	8.8	5.2	15.9	14.9	10.9

The potential impact of the presence of near density material on DMS performance is presented in Table IV, based on the HLS results. A potential change in the 1st Pass DMS SG cut-point (2.70 +/- 0.02) in the first pass could result in lithium recoveries to the DMS sinks between 93% and 96% at mass recoveries between 43% and 35%. A similar fluctuation of the Pass SG-cut-point (2.90 +/- 0.02) could produce final DMS concentrate grades between 5.8% Li₂O and 6.1% Li₂O (+/- 0.1% Li₂O) with lithium recoveries varying between 79% and 82%.

Table IV: Potential Impact of Near Density Material on DMS (Before Magnetic Separation)

1st pass - Stage					
SG Cut	Weight	Assay %		Distribution %	
	%	Li ₂ O	Fe ₂ O ₃	Li	Fe ₂ O ₃
2.68 (-0.02)	42.7	3.43	1.47	96.1	75.9
2.70	37.6	3.78	1.58	95.0	72.9
2.72 (+0.02)	35.1	4.06	1.62	93.1	69.1
2nd pass Stage					
SG Cut	Weight	Assay %		Distribution %	
	%	Li ₂ O	Fe ₂ O ₃	Li	Fe ₂ O ₃
2.88 (-0.02)	53.3	5.84	1.70	82.2	57.4
2.90	51.3	5.94	1.69	80.5	54.7
2.92 (+0.02)	49.1	6.05	1.67	78.5	51.7

As noted, the DMS feed was crushed to 100% passing -9.5 mm and the -0.85 mm fraction was screened out and reserved for flotation testwork. The +0.85 mm fraction was sent to DMS. The DMS test was performed in two stages. The first pass was at the lower SG cut-point of 2.70 to reject silicate gangue and the second pass was at an SG cut-point of 2.90 to generate spodumene concentrate.

Following DMS, the DMS concentrate was passed through dry magnetic separation to generate final product, while the DMS middlings and -0.85 mm fraction were combined as the flotation feed. The final non-magnetic DMS concentrate graded 6.5% Li₂O and 0.98% Fe₂O₃ at a global lithium recovery of 67.5% (Table V). The metallurgical target grade of > 6.0% Li₂O and <1.0% Fe₂O₃ was achieved, proving the amenability of this material (after ore sorting) to DMS. The head assay of the resulting flotation feed was ~1.45% Li₂O and it contained ~25% of the total lithium distribution.

Table V: Summary of DMS Results

Combined DMS Products	Wt.	Assay (%)											Distribution (%)									
	%	Li	Li ₂ O	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	P ₂ O ₅	MnO	Li	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	P ₂ O ₅	
DMS Conc. (Non Mag)	15.0	3.03	6.52	64.4	25.2	0.98	0.14	0.16	0.69	0.45	0.10	0.13	67.5	13.1	23.3	18.9	10.0	6.0	2.2	4.2	10.8	
Mag Conc.	1.5	0.72	1.54	49.9	23.3	8.98	1.50	3.22	1.49	3.17	1.23	0.72	1.6	1.1	2.2	17.9	11.0	12.3	0.5	3.1	14.3	
DMS Middlings	11.4	0.83	1.77	70.8	17.9	1.48	0.28	0.64	3.50	1.76	0.17	0.10	14.1	11.0	12.7	21.7	15.4	17.9	8.7	12.6	14.3	
DMS Tailings	58.7	0.07	0.14	76.8	13.6	0.25	0.15	0.30	5.98	1.80	0.10	0.02	5.8	61.4	49.2	18.8	41.8	43.2	76.6	65.9	43.9	
DMS U/S	2.0	0.80	1.72	70.0	17.4	1.53	0.30	0.61	3.29	2.08	0.15	0.09	2.4	1.9	2.1	3.9	2.8	3.0	1.4	2.6	2.2	
-0.85 mm frac.	11.4	0.51	1.10	74.0	14.9	1.29	0.35	0.63	4.22	1.64	0.17	0.08	8.6	11.5	10.5	18.8	18.9	17.6	10.5	11.7	14.5	
Feed (Cal.)	100	0.67	1.44	73.4	16.2	0.78	0.21	0.41	4.58	1.60	0.13	0.06	100	100	100	100	100	100	100	100	100	
Feed (Dir.)		0.66	1.42	73.2	16.3	0.77	0.20	0.39	4.51	1.62	0.13	0.07										
Flotation Feed (Dir.)		0.67	1.44	72.3	16.4	1.34	0.31	0.65	3.82	1.66	0.17	0.09										
Flotation Feed (Cal.)	24.8	0.68	1.46	72.2	16.5	1.39	0.32	0.63	3.81	1.73	0.17	0.09	25.1	24.4	25.2	44.4	37.2	38.5	20.7	26.8	31.0	

Flotation testwork was performed to recover additional spodumene from the DMS middlings and -0.85 mm fines and produce additional concentrate. The flotation feed was stage-ground to P100 of 300 μm and two batch flotation tests were performed. The flotation flowsheet included magnetic separation, desliming, mica flotation, and spodumene flotation. Magnetic separation was also performed on the spodumene flotation concentrate, when necessary. Flotation results indicated that a collector dosage of 500 g/t FA2/TPA100 in the rougher provided the best flotation stage lithium recovery of 66% and concentrate grade in the 3rd cleaner concentrate (non-mag) of 6.22% Li₂O. It is worth highlighting that the 2nd cleaner concentrate also met the >6.0% Li₂O concentrate specifications at a grade of 6.05% Li₂O and a lithium recovery of 71%, with an iron content very close to the cut-off limit (1.03% Fe₂O₃). Consequently, the final developed flowsheet needs to incorporate only two cleaning stages in the spodumene flotation circuit without the need for further magnetic separation on the flotation concentrate.

From the testwork program, the flowsheet shown in Figure I was developed. In addition, Bilmat (mass balancing software) was used to confirm the accuracy of the testwork results and aid in the overall metallurgical balance. The Bilmat results are summarized in Table VI. With the developed flowsheet, this testwork program showed that 83.5% of the lithium can be recovered at the metallurgical target grade of >6% Li₂O and < 1% Fe₂O₃ using a combination of DMS and flotation.

Table VI: Summary of Mass Balance from Bilmat

Streams	Mass	Assay %										Distribution %								
	%	Li ₂ O	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	P ₂ O ₅	Li ₂ O	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	P ₂ O ₅	
Composite Head Sample	100	1.24	71.2	16.2	2.08	0.48	1.16	4.28	1.74	0.14	100	100	100	100	100	100	100	100	100	
Waste Head Sample	17.6	0.21	60.2	16.0	8.49	1.88	5.01	2.90	2.51	0.23	3.0	14.8	17.3	71.6	68.0	75.8	11.9	25.3	28.4	
Pegmatite Head Sample	82.5	1.46	73.5	16.3	0.72	0.19	0.34	4.57	1.58	0.12	97.0	85.2	82.7	28.4	32.0	24.2	88.1	74.7	71.6	
Coarse (+1/2") Waste Frac	16.7	0.22	60.2	16.0	8.43	1.86	4.97	2.90	2.55	0.23	2.9	14.1	16.5	67.8	64.1	71.6	11.3	24.5	27.2	
Fine (-1/2") Waste Frac	0.8	0.15	59.0	15.5	9.64	2.24	5.81	2.87	1.70	0.20	0.1	0.7	0.8	3.9	3.9	4.2	0.6	0.8	1.2	
Coarse (+1/2") Peg Frac	68.0	1.62	73.4	16.7	0.68	0.17	0.32	4.54	1.53	0.13	88.8	70.1	70.0	22.2	23.2	19.0	72.2	59.8	60.7	
Fine (-1/2") Peg Frac	14.4	0.71	74.2	14.2	0.88	0.30	0.42	4.73	1.80	0.11	8.2	15.0	12.6	6.1	8.8	5.2	15.9	14.9	10.9	
Ore Sorter Product	68.2	1.62	73.3	16.7	0.68	0.16	0.33	4.53	1.53	0.13	88.8	70.2	70.2	22.3	23.1	19.7	72.2	59.9	61.2	
Ore Sorter Reject	16.6	0.21	60.2	16.0	8.49	1.88	4.96	2.90	2.56	0.23	2.9	14.0	16.4	67.7	64.3	71.0	11.3	24.4	26.7	
DMS Feed	83.4	1.45	73.3	16.3	0.81	0.21	0.40	4.55	1.58	0.13	97.1	86.0	83.6	32.3	35.7	29.0	88.7	75.6	73.3	
DMS Feed Coarse	72.4	1.49	73.3	16.4	0.71	0.19	0.36	4.62	1.57	0.12	86.9	74.6	73.4	24.9	27.8	22.7	78.2	65.3	62.1	
DMS Feed U/S	11.0	1.15	73.3	15.1	1.40	0.35	0.66	4.07	1.62	0.14	10.2	11.4	10.3	7.4	7.9	6.3	10.5	10.3	11.2	
DMS 1st Pass Float	48.6	0.14	76.8	13.7	0.25	0.15	0.29	5.97	1.79	0.10	5.6	52.4	41.0	5.8	14.6	12.1	67.8	50.0	33.9	
DMS 1st Pass Sink	23.8	4.25	66.3	22.0	1.67	0.27	0.52	1.87	1.12	0.17	81.3	22.1	32.3	19.1	13.2	10.6	10.4	15.3	28.2	
DMS 2nd Pass Float	9.7	1.68	70.7	17.6	1.59	0.29	0.69	3.54	1.76	0.15	13.1	9.6	10.5	7.4	5.8	5.8	8.0	9.8	10.5	
DMS 2nd Pass Sink	14.1	6.02	63.3	25.1	1.72	0.25	0.40	0.72	0.68	0.18	68.3	12.5	21.8	11.7	7.4	4.9	2.4	5.5	17.7	
DMS Mag Conc	1.2	1.54	49.9	23.3	9.38	1.50	3.12	1.48	3.16	1.15	1.5	0.8	1.7	5.4	3.8	3.3	0.4	2.2	9.8	
DMS NonMag Conc	12.9	6.45	64.5	25.2	1.01	0.14	0.15	0.65	0.44	0.09	66.8	11.7	20.0	6.2	3.7	1.6	2.0	3.3	7.9	
Flot Feed	20.7	1.39	72.1	16.3	1.49	0.32	0.67	3.82	1.69	0.15	23.2	21.0	20.8	14.8	13.7	12.1	18.5	20.1	21.7	
WHIMS Mag Conc	1.2	1.20	45.7	21.4	13.0	2.32	3.13	1.62	2.26	0.68	1.2	0.8	1.6	7.8	5.9	3.4	0.5	1.6	6.0	
WHIMS NonMag Prod	19.5	1.41	73.8	15.9	0.75	0.19	0.52	3.96	1.65	0.11	22.0	20.2	19.2	7.1	7.7	8.7	18.0	18.5	15.7	
1st slimes	1.8	0.97	66.1	18.9	1.69	0.65	0.98	3.95	2.80	0.16	1.4	1.7	2.1	1.5	2.4	1.5	1.7	2.9	2.1	
1st Deslimed Prod	17.7	1.45	74.5	15.7	0.66	0.15	0.47	3.96	1.53	0.11	20.6	18.5	17.1	5.6	5.3	7.2	16.4	15.6	13.7	
Mica Conc	1.7	0.95	54.6	27.3	2.33	0.29	0.56	1.86	7.41	0.25	1.3	1.3	2.9	1.9	1.0	0.8	0.7	7.3	3.0	
Mica Tailings	16.0	1.50	76.7	14.4	0.48	0.13	0.46	4.19	0.90	0.10	19.3	17.2	14.2	3.7	4.3	6.4	15.6	8.3	10.7	
2nd slimes	0.3	1.05	69.3	16.4	1.01	0.64	1.55	4.25	1.52	0.12	0.3	0.3	0.3	0.2	0.4	0.5	0.3	0.3	0.3	
2nd Deslimed Prod	15.6	1.51	76.8	14.4	0.47	0.12	0.44	4.19	0.89	0.09	19.0	16.9	13.9	3.5	3.9	5.9	15.3	8.0	10.4	
Spod Ro Conc	4.3	5.31	64.3	23.5	0.97	0.29	1.03	1.34	0.50	0.28	18.4	3.9	6.2	2.0	2.6	3.8	1.3	1.2	8.6	
Spod Ro Tail	11.3	0.07	81.6	10.9	0.28	0.05	0.21	5.27	1.04	0.02	0.7	13.0	7.6	1.5	1.3	2.1	14.0	6.8	1.8	
Spod Scav Conc	0.2	1.94	70.1	18.0	1.12	0.28	0.72	3.63	1.35	0.04	0.3	0.2	0.2	0.1	0.1	0.1	0.2	0.2	0.1	
Spod Scav Tail	11.1	0.04	81.8	10.8	0.26	0.05	0.20	5.30	1.04	0.02	0.4	12.8	7.4	1.4	1.2	1.9	13.8	6.6	1.8	
Spod Cl Conc	3.4	6.17	62.6	24.9	1.03	0.29	1.13	0.69	0.33	0.35	16.7	3.0	5.2	1.7	2.0	3.3	0.5	0.6	8.3	
Spod Cl Tail	0.9	2.19	70.6	18.3	0.78	0.29	0.70	3.67	1.10	0.04	1.6	0.9	1.1	0.3	0.6	0.6	0.8	0.6	0.3	
Combined Flot and DMS Conc	16.2	6.39	64.1	25.2	1.01	0.17	0.35	0.66	0.42	0.14	83.5	14.6	25.2	7.9	5.7	4.9	2.5	3.9	16.2	





Figure I: Overall Process Flowsheet

Qualified Person Statement

Mr Brent Hilscher P.Eng., Vice President of ABH Engineering Inc., who reviewed the studies and test work conducted by SGS on behalf of Snow Lake Resources compiled and evaluated the technical information in this release and is satisfied with the results. Mr Hilscher does not take responsibility for test work and is a member of the Association of Engineers and Geoscientists of British Columbia (EGBC), which is ROPO, accepted for the purpose of reporting in accordance with SK-1300. Mr Hilscher has sufficient experience relevant to Lithium and Lithium technology and processing to qualify as a qualified Person as defined under SK-1300 guidelines. Mr Hilscher consents to the inclusion in the report of the matters based on information in the form and context in which it appears based off SGS test work.

About Snow Lake Resources Ltd.

Snow Lake is committed to near term production and cash flow lithium mine through conventional truck and shovel mining methods to supply the North American electric vehicle and battery markets.

Our wholly owned Snow Lake Lithium™ Project now covers a 59,587-acre site that has only been 1% explored and contains an identified-to-date 11.1 million metric tonnes indicated and inferred resource at 1% Li₂O.

Forward-looking Statements

This press release contains "forward-looking statements" that are subject to substantial risks and uncertainties. All statements, other than statements of historical fact, contained in this press release are forward-looking statements, including without limitation statements with restoring Snow Lake Lithium. We base these forward-looking statements on our expectations and projections about future events, which we derive from the information currently available to us. Forward-looking statements contained in this press release may be identified by the use of words such as "anticipate," "believe," "contemplate," "could," "estimate," "expect," "intend," "seek," "may," "might," "plan," "potential," "predict," "project," "target," "aim," "should," "will," "would," or the negative of these words or other similar expressions, although not all forward-looking statements contain these words. Forward-looking statements are based on Snow Lake Resources Ltd.'s current expectations and are subject to inherent uncertainties, risks and assumptions that are difficult to predict. Further, certain forward-looking statements are based on assumptions as to future events that may not prove to be accurate. Some of these risks and uncertainties are described more fully in the section titled "Risk Factors" in our registration statements and reports filed with the Securities and Exchange Commission. Forward-looking statements contained in this announcement are made as of this date, and Snow Lake Resources Ltd. undertakes no duty to update such information except as required under applicable law.

For more information, please contact:

Investors: ir@snowlakelithium.com

Media: media@snowlakelithium.com

Twitter: [@SnowLakeLithium](https://twitter.com/SnowLakeLithium)

www.SnowLakeLithium.com

SOURCE: Snow Lake Resources Ltd.
